


TEST REPORT

BonaKemi AB
Malmö, Sweden

**Sliding properties of a parquet lacquer
according to DIN V 18 032-2 (April 2001)**

| | |
|--------------------|--------------|
| Date of the report | : 05-15-2002 |
| Subject | : 46/03/Kn/C |
| Pages | : 3 |
| Annexes | : 0 |

The last page and the annex are signed with our seal. The duplication and publishing of the test report in complete or shortened wording as well as for sales promotion is only allowed by our written permission.
Venue and domicile is Stuttgart.



Test report 46/03 dated 05-15-2002

BonaKemi AB
P.O. Box 21074

200 21 Malmö
Sweden

Our reference : 46/03/Kn/C

Subject : Test of the sliding properties of a parquet lacquer
according to DIN V 18 032-2 (April 2001)

We have been commissioned by BonaKemi AB, Malmö, to test the sliding properties of the parquet lacquer

„BonaTech Freshen Up“

according to DIN V 18 032-2 (April 2001).

For the tests we got 5 parquet samples which have been sealed with the lacquer mentioned above.

The following results were obtained:





Test report 46/03 dated 05-15-2002

| test spot no. | sliding coefficient μ |
|---------------|---------------------------|
| 1 | 0,42 |
| 2 | 0,41 |
| 3 | 0,40 |
| 4 | 0,43 |
| 5 | 0,42 |

The requirements of DIN V 18 032-2 (April 2001) regarding the sliding properties of μ min. 0,4; μ max. 0,6 were met by the parquet lacquer „**BonaTech Freshen Up**“.


Schmid
Tester




Dipl.-Ing. Knauf
Section Leader